



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 101 530 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
23.05.2001 Bulletin 2001/21

(51) Int Cl.7: B01J 23/74, C10G 45/06

(21) Application number: 99203876.0

(22) Date of filing: 19.11.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: Kramer, Lucas Laurentius
3471 AJ Kamerik (NL)

(74) Representative: Ottevangers, Sietse Ulbe et al
Vereenigde,
Postbus 87930
2508 DH Den Haag (NL)

(71) Applicant: ENGELHARD CORPORATION
Iselin, New Jersey 08830-0770 (US)

(54) Nickel-iron containing hydrogenation catalyst

(57) The invention is directed to a catalyst suitable for the hydrogenation of hydrocarbon resins, comprising a supported nickel on silica and alumina catalyst, said catalyst having a nickel content of 45 to 85 wt.%, a silicon content, calculated as SiO₂, of 14 to 45 wt.%, an

aluminium content, calculated as Al₂O₃, of 1 to 15 wt.% an iron content, calculated as Fe, 0.25 to 4 wt.%, all percentages having been calculated on the basis of the reduced catalyst, and which catalyst has a pore volume between 2 and 60 nm, as defined herein, of at least 0.35 ml/g of catalyst.

EP 1 101 530 A1

Description

[0001] The invention relates to a catalyst for hydrogenating hydrocarbon resins. Hydrocarbon resins are produced by oligomerisation or polymerisation of hydrocarbon fractions, typically originating from the (catalytic) cracking of crude, including petroleum distillates and fractions from naphtha crackers, and tend to contain impurities, including so-called color bodies, and other impurities including sulfur compounds, nitrogen compounds, chlorine compounds and/or fluorine compounds. In order to give the resins the required properties (chemical and physical), they are usually hydrogenated using conventional hydrogenation catalysts, such as nickel or precious metal catalysts.

[0002] The hydrogenation step can be used to modify various properties of the hydrocarbon resin depending on the properties of the resin to be hydrogenated and the requirements put on the final resin. Examples of these modifications are removal of part or all of the aromatic moieties, removal of so-called color bodies (i.e. decolorizing the resin from yellow to colorless), modification of the molecular weight distribution (decrease of average molecular weight) and removal of impurities, such as sulfur, nitrogen and/or halogen compounds.

[0003] Typical prior art nickel hydrogenation catalysts tend to have a very low activity in the molecular weight modification at mild reaction conditions.

[0004] Accordingly there is a need for a catalyst and process wherein it is possible to obtain good catalytic activity in hydrogenation of hydrocarbon resins, providing a good balance of properties. Further there is a need for a catalyst that makes it possible to steer the balance of properties of the resulting hydrogenated hydrocarbon resin in terms of molecular weight and/or color and/or chemical composition, in dependence of the wish of the end user and/or the original composition of the hydrocarbon resin, while maintaining good activity of the catalyst, or even improving it.

[0005] Accordingly it is an object of the invention to provide a catalyst and process for the hydrogenation of hydrocarbon resins, wherein these advantages are obtained. A further object is to provide a process for the preparation of such a catalyst.

[0006] The invention provides a catalyst suitable for the hydrogenation of hydrocarbon resins, comprising a supported nickel on silica and alumina catalyst, said catalyst having a nickel content of 45 to 85 wt.%, a silicium content, calculated as SiO_2 , of 14 to 45 wt.%, an aluminium content, calculated as Al_2O_3 , of 1 to 15 wt.% an iron content, calculated as Fe, 0.25 to 4 wt.%, all percentages having been calculated on the basis of the reduced catalyst, and which catalyst has a pore volume between 2 and 60 nm, as defined herein, of at least 0.35 ml/g of catalyst.

[0007] Surprisingly it has been found that this catalyst provides a good hydrogenation of hydrocarbon resins, both in terms of activity and in the possibility of steering the properties of the hydrocarbon resin in order to obtain useful properties in the hydrogenated resin.

[0008] Surprisingly it has been found that with the catalyst of the present invention, among others characterized by the specific support material, active components and pore distribution, it is possible to steer the cracking behavior of the catalyst. In case magnesium is present in the catalyst, the cracking is suppressed, whereas without magnesium the catalyst shows good cracking behavior, without sacrificing the activity. This is quite surprising, as with other catalysts this influence of the presence or absence of magnesium is not found (or to a much lesser degree). The magnesium is present in the catalyst in amounts of up to 2.5 wt.%, calculated as metal. It is expected that the magnesium will be present as oxide, in view of the chemical properties of magnesium. Accordingly it is a feature of the present invention that by selection of the amount of this compound, the cracking of the resin may be influenced and as a consequence the average molecular weight of the resulting resin.

[0009] The catalyst of the present invention has a total pore volume (cylindrical pores, nitrogen adsorption pore diameters of 2 to 60 nm) of at least 0.35 ml/g of catalyst.

[0010] To determine the total pore volume an accurately weighed sample is degassed in a special sample vessel under vacuum at a temperature of 105-220°C in order to remove adsorbed vapors from the surface. Subsequently the sample vessel is immersed in a liquid nitrogen bath, causing adsorption and condensation of nitrogen, which is introduced in small known quantities, using the Quantachrome Autosorb-6.

The recording of the adsorption isotherm is followed by the recording of the desorption isotherm by removing the nitrogen in small known quantities. The desorption isotherm is utilized to calculate the nitrogen pore volume distribution using the BJH-method.

[0011] The Loose Apparent Bulk Density (LABD, is the density of powder, measured in 100 ml cylindrical measuring flask after 10 minutes settling without any external force) is preferably less than 0.30 g/ml

[0012] The nickel content of the catalyst, based on the weight of the reduced catalyst is between 45 and 85 wt.%, with a preference for a value between 55 and 75 wt.%. Within these ranges the optimum for activity and selectivity is obtained. The support material is a combination of silica and alumina. This may be a mixture of the two components, but is also possible that the silicium and aluminium ions are at least partly in the same crystal lattice.

[0013] The catalyst according to the invention can be prepared by various methods, such as impregnation of the active components on a preformed silica and alumina containing support, or precipitation on the said support.

[0014] It is, however, preferred to prepare the supported catalyst by coprecipitation. This comprises precipitating the

catalyst components (catalyst precursor) from solutions of nickel salt, iron salt, aluminium salt and silicium compound, and optional other components, usually by raising or maintaining the pH above about 7.5 by adding a lye, urea, or by electrochemical means. Usual techniques may be applied herein, such as adding all solutions at the same time to the precipitation vessel, or providing one or more components therein and adding the others to the vessel.

[0015] The present invention is accordingly also directed to a process for preparing a supported nickel on silica and alumina catalyst, said catalyst having a nickel content of 45 to 85 wt.%, a silicium content, calculated as SiO_2 , of 14 to 45 wt.%, an aluminium content, calculated as Al_2O_3 , of 1 to 15 wt.% an iron content, calculated as Fe, 0.25 to 4 wt.%, all percentages having been calculated on the basis of the reduced catalyst, and which catalyst has a pore volume between 2 and 60 nm, as defined herein, of at least 0.35 ml/g of catalyst, said process comprising coprecipitating the catalyst components at a pH-value of at least 7.5, recovering the coprecipitated material from the precipitation liquid, washing it and further treating it to produce the catalyst.

[0016] The precipitate is subsequently filtered off, washed and further treated as need be. This may include calcination, reduction and passivation. In case magnesium is present in the catalyst this may be included in the solution from which the catalyst is precipitated.

[0017] In the present invention various hydrocarbon resin feedstocks may be used. A general definition of hydrocarbon resins has been given in ISO 472, namely products produced by polymerization from coal tar, petroleum and turpentine feedstocks. Preferred are petroleum distillates, resins, and the like. It is possible to use these feedstocks directly, but it is also possible to use the product from a previous hydrodesulfurisation process, i.e. a feedstock having a reduced sulfur content, for example in the range of up to 500 ppm, preferably up to 300 ppm.

[0018] The process according to the invention comprises hydrogenating the hydrocarbon resin using the catalyst described above. Suitable temperatures and pressures are based on the properties of the resin, the properties required of the end-product and the actual composition and structure of the catalyst. Suitable temperatures are between 100 and 350°C, with a preference for temperatures between 250 and 325°C; partial hydrogen pressures can be between 1 and 150 bar (abs), and the hydrogenation time is mainly dependent on the temperature, amount of catalyst and required degree of hydrogenation of the resin.

[0019] The process is preferably carried out in batch, wherein the catalyst is dispersed in the hydrocarbon resin as powder. Suitable particle sizes of powder are between 1 and 1000 μm . The consumption of fresh catalyst in the process is usually between 0.25 and 4 wt.% relative to the resin.

[0020] The process can be carried out in various reactors suitable for slurry hydrogenation, such as stirred tank reactors (optionally cascaded) or loop reactors.

[0021] Use of the catalyst as described above results in a hydrogenation of hydrocarbon resins to a product having a carefully balanced set of properties, both chemically and physically. At the same time the hydrogenation results in a decrease of the amount of impurities in the final product.

[0022] The present invention is now elucidated on the basis of the following example.

EXAMPLES

EXAMPLE 1

[0023] Solutions containing nickel and magnesium salts, silicate and sodium carbonate were mixed in a well stirred precipitation vessel at a temperature of 80°C.

The pH of the slurry formed was about 7.5 and after 1 hour the precipitation was completed.

After washing the precipitate, the precursor of the catalyst was filtered and dried in an oven at 110°C. The catalyst was activated at with hydrogen.

The composition and the physical properties of the resulting catalyst are specified in table 1.

EXAMPLE 2

[0024] Solutions containing nickel and iron(III) salts, silicate, aluminate and sodium carbonate were mixed in a well stirred precipitation vessel at a temperature of 80°C. The pH of the slurry formed was about 7.5 and after 1 hour the precipitation was completed.

After washing the precipitate, the precursor of the catalyst was filtered and dried in an oven at 110°C. The catalyst was activated with hydrogen.

The composition and the physical properties of the resulting catalyst are specified in table 1.

EXAMPLE 3

[0025] Solutions containing nickel, iron(III) and magnesium salts, silicate, aluminate and sodium carbonate were

mixed in a well stirred precipitation vessel at a temperature of 80°C.

The pH of the slurry formed was about 7.5 and after 1 hour the precipitation was completed.

After washing the precipitate, the precursor of the catalyst was filtered and dried in an oven at 110°C. The catalyst was activated with hydrogen.

The composition and the physical properties of the resulting catalyst are specified in table 1.

EXAMPLE 4

[0026] 500 g of a 50 wt% hydrocarbon resin (containing 75 ppm S compounds) solution in Shellsol D40 mixed with 3.75 grams of a nickel catalyst was heated in a 1 liter autoclave under 2 bars hydrogen and agitated at 1400 rpm.

As soon as a temperature reached 275°C, the hydrogen pressure was increased to 90 bar. The subsequent hydrogenation process was monitored by recording the hydrogen consumption. The activity of the catalyst on resin hydrogenation, is expressed as the reaction rate constant, obtained from linear regression between 40% and 70% conversion. At 70% conversion the resin mixture is filtered and the molecular weight distribution is determined by means of GPC. The cracking level can be expressed as the reduction of the average molecular weight compared to the original resin feed.

The catalysts described in example 1, 2 and 3 were subject to the above described activity test. The results of these tests are specified in table 1.

Table 1

		Example 1	Example 2	Example 3
Ni	Wt.-%	62	62	60
Mg	Wt.-%	2.8	0	2.0
Fe	Wt.-%	0	1.5	0.8
SiO ₂	Wt.-%	11	22	18
Al ₂ O ₃	Wt.-%	0	3.1	3.0
Pore Volume (2-60 nm)	ml/g	0.30	0.66	0.45
LABD	g/ml	0.32	0.21	0.29
Reaction rate constant resin hydrogenation	mol H ₂ /h/h	2.0	6.1	5.8
Reduction of average molecular weight	%	3	16	0

Claims

1. Catalyst suitable for the hydrogenation of hydrocarbon resins, comprising a supported nickel on silica and alumina catalyst, said catalyst having a nickel content of 45 to 85 wt.%, a silicium content, calculated as SiO₂, of 14 to 45 wt.%, an aluminium content, calculated as Al₂O₃, of 1 to 15 wt.% an iron content, calculated as Fe, 0.25 to 4 wt.%, all percentages having been calculated on the basis of the reduced catalyst, and which catalyst has a pore volume between 2 and 60 nm, as defined herein, of at least 0.35 ml/g of catalyst.
2. Catalyst according to claim 1, wherein additionally up to 2.5 wt.% magnesium, at least partly in the form of oxide is present in the catalyst.
3. Catalyst according to claim 1 or 2, wherein the nickel content is between 55 and 75 wt.% of the reduced catalyst.
4. Catalyst according to claims 1-3, wherein the catalyst is a coprecipitated catalyst.
5. Process for the hydrogenation of hydrocarbon resins in the presence of a supported nickel catalyst, wherein the hydrogenation is performed in the presence the catalyst according to any one of the claims 1-4.
6. Process according to claim 5, wherein the color bodies present in the resin are hydrogenated.

7. Process according to claim 5 or 6, wherein the molecular weight distribution of the resin is influenced by the composition of the catalyst.
8. Process according to claims 5-7, wherein sulfur, halogen and/or nitrogen impurities are at least partly removed from the resin.
9. Process for the preparation of a supported nickel on silica and alumina catalyst, said catalyst having a nickel content of 45 to 85 wt.%, a silicium content, calculated as SiO_2 , of 14 to 45 wt.%, an aluminium content, calculated as Al_2O_3 , of 1 to 15 wt.% an iron content, calculated as Fe, 0.25 to 4 wt.%, all percentages having been calculated on the basis of the reduced catalyst, and which catalyst has a pore volume between 2 and 60 nm, as defined herein, of at least 0.35 ml/g of catalyst, which process comprises coprecipitating the catalyst components at a pH-value of at least 7.5, recovering the coprecipitated material from the precipitation liquid, washing it and further treating it to produce the catalyst.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 20 3876

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 5 356 847 A (HENDERSON JOHN H) 18 October 1994 (1994-10-18)		B01J23/74 C10G45/06
A	US 4 532 351 A (BARNETT ALLAN E ET AL) 30 July 1985 (1985-07-30)		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B01J C10G
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 11 April 2000	Examiner Schwaller, J-M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 20 3876

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

11-04-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5356847 A	18-10-1994	EP 0597662 A	18-05-1994
		JP 6205978 A	26-07-1994
		US 5493037 A	20-02-1996
US 4532351 A	30-07-1985	AU 565181 B	10-09-1987
		AU 1580883 A	22-12-1983
		CA 1196906 A	19-11-1985
		EP 0097047 A	28-12-1983
		IN 159334 A	02-05-1987
		JP 59016542 A	27-01-1984

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)